



FIBERCON

It is a monofilament polypropylene fiber. It is dispersed in a cement mixture to improve permeability and enhance service life of concrete by preventing formation of cracks due to moisture lost, plastic shrinkage and settlement cracks.

ADVANTAGES

- Prevent formation of microcracks
- Improve permeability of concrete
- Increase cohesiveness
- Control bleeding of water

SPECIFICATION

Material	Polypropylene
Length	6mm for plaster 12mm for concrete
Density	0.91
Dispersion	High

MIXING AND APPLICATION

Follow dosage and add after cement, sand and water has already been initially mixed. Mix at a medium speed. The shortest possible mixing until desired paste is achieved to avoid damaging the fiber.

DOSAGE

0.03 - 0.06% (72g - 144g) per plaster weight
0.02 - 0.05% (350g - 820g) per concrete weight

PACKAGING

72g and 820g per bag

T: +63.2.932.8806 / +63.2.931.3822 • F: +63.2.875.7173
www.betonitproducts.com



FIBERCON

It is a monofilament polypropylene fiber. It is dispersed in a cement mixture to improve permeability and enhance service life of concrete by preventing formation of cracks due to moisture lost, plastic shrinkage and settlement cracks.

ADVANTAGES

- Prevent formation of microcracks
- Improve permeability of concrete
- Increase cohesiveness
- Control bleeding of water

SPECIFICATION

Material	Polypropylene
Length	6mm for plaster 12mm for concrete
Density	0.91
Dispersion	High

MIXING AND APPLICATION

Follow dosage and add after cement, sand and water has already been initially mixed. Mix at a medium speed. The shortest possible mixing until desired paste is achieved to avoid damaging the fiber.

DOSAGE

0.03 - 0.06% (72g - 144g) per plaster weight
0.02 - 0.05% (350g - 820g) per concrete weight

PACKAGING

72g and 820g per bag

T: +63.2.932.8806 / +63.2.931.3822 • F: +63.2.875.7173
www.betonitproducts.com